

SABIC CYCOLAC™ ABS MG37EPX物性表

属性	典型值	UNITS	测试手段
MECHANICAL			
Tensile Stress, yield, 5 mm/min	48	MPa	ISO 527
Tensile Stress, break, 5 mm/min	39	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	2	%	ISO 527
Tensile Strain, break, 5 mm/min	15.8	%	ISO 527
Tensile Modulus, 1 mm/min	2760	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	73	MPa	ISO 178
Flexural Modulus, 2 mm/min	2470	MPa	ISO 178
IMPACT			
Izod Impact, notched 80*10*4 +23°C	23	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	8	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 -40°C	6	kJ/m ²	ISO 180/1A
THERMAL			
CTE, -40°C to 40°C, flow	6.E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	6.E-05	1/°C	ISO 11359-2
Vicat Softening Temp, Rate B/50	98	°C	ISO 306
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	82	°C	ISO 75/Af
PHYSICAL			
Mold Shrinkage, flow, 3.2 mm	0.4-0.6	%	SABIC method
Melt Flow Rate, 220°C/10.0 kgf	20.6	g/10 min	ASTM D1238
Density	1.05	g/cm ³	ISO 1183
Injection Molding			
Drying Temperature	80-95	°C	
Drying Time	2-4	Hrs	
Drying Time (Cumulative)	8	Hrs	
Maximum Moisture Content	0.05	%	
Melt Temperature	255-280	°C	

Nozzle Temperature	255-280	°C
Front - Zone 3 Temperature	250-270	°C
Middle - Zone 2 Temperature	230-245	°C
Rear - Zone 1 Temperature	215-230	°C
Mold Temperature	40-80	°C
Back Pressure	0.3-0.7	MPa
Screw Speed	30-60	rpm
Shot to Cylinder Size	50-70	%
Vent Depth	0.038-0.051	mm

此数据由我们从该材料的生产商处获得。我们尽最大努力确保此数据的准确性，但是我们对这些数据值不承担任何责任，并强烈建议在最终选料前，就数据值与材料供应商进行验证。