

SABIC LEXAN™ PC PC0703物性表

| 属性 | 典型值 | UNITS | 测试手段 |
|--|------|-------------------|------------|
| MECHANICAL | | | |
| Tensile Stress, yld, Type I, 50 mm/min | 63 | MPa | ASTM D638 |
| Tensile Strain, yld, Type I, 50 mm/min | 6 | % | ASTM D638 |
| Tensile Strain, brk, Type I, 50 mm/min | >70 | % | ASTM D638 |
| Tensile Modulus, 50 mm/min | 2350 | MPa | ASTM D638 |
| Flexural Stress, yld, 1.3 mm/min, 50 mm span | 90 | MPa | ASTM D790 |
| Flexural Modulus, 1.3 mm/min, 50 mm span | 2300 | MPa | ASTM D790 |
| Hardness, Rockwell R | 120 | - | ASTM D785 |
| Tensile Stress, yield, 50 mm/min | 63 | MPa | ISO 527 |
| Tensile Strain, yield, 50 mm/min | 6 | % | ISO 527 |
| Tensile Strain, break, 50 mm/min | >70 | % | ISO 527 |
| Tensile Modulus, 1 mm/min | 2350 | MPa | ISO 527 |
| Flexural Stress, yield, 2 mm/min | 90 | MPa | ISO 178 |
| Flexural Modulus, 2 mm/min | 2300 | MPa | ISO 178 |
| Hardness, Rockwell R | 120 | - | ISO 2039-2 |
| IMPACT | | | |
| Izod Impact, unnotched, 23°C | NB | J/m | ASTM D4812 |
| Izod Impact, notched, 23°C | 900 | J/m | ASTM D256 |
| Instrumented Dart Impact Energy @ peak, 23°C | 65 | J | ASTM D3763 |
| Izod Impact, unnotched 80*10*3 +23°C | NB | kJ/m ² | ISO 180/1U |
| Izod Impact, unnotched 80*10*3 -30°C | NB | kJ/m ² | ISO 180/1U |
| Izod Impact, notched 80*10*3 +23°C | 70 | kJ/m ² | ISO 180/1A |
| Izod Impact, notched 80*10*3 -30°C | 12 | kJ/m ² | ISO 180/1A |
| THERMAL | | | |
| Vicat Softening Temp, Rate B/50 | 144 | °C | ASTM D1525 |

| | | | |
|---|--------|--------|----------------|
| HDT, 0.45 MPa, 3.2 mm | 138 | °C | ASTM D648 |
| HDT, 1.82 MPa, 3.2 mm | 127 | °C | ASTM D648 |
| CTE, -40°C to 95°C, flow | 7.E-05 | 1/°C | ASTM E831 |
| Thermal Conductivity | 0.2 | W/m-°C | ASTM C177 |
| Thermal Conductivity | 0.2 | W/m-°C | ISO 8302 |
| CTE, 23°C to 80°C, flow | 7.E-05 | 1/°C | ISO 11359-2 |
| Ball Pressure Test, 125°C +/- 2°C | Passes | - | IEC 60695-10-2 |
| Vicat Softening Temp, Rate B/50 | 144 | °C | ISO 306 |
| HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm | 138 | °C | ISO 75/Bf |
| HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm | 127 | °C | ISO 75/Af |

PHYSICAL

| | | | |
|--|---------|-------------------------|--------------|
| Specific Gravity | 1.2 | - | ASTM D792 |
| Water Absorption, (23°C/Saturated) | 0.35 | % | ASTM D570 |
| Mold Shrinkage on Tensile Bar, flow | 0.5-0.7 | % | SABIC method |
| Mold Shrinkage, flow, 3.2 mm | 0.5-0.7 | % | SABIC method |
| Melt Flow Rate, 300°C/1.2 kgf | 7 | g/10 min | ASTM D1238 |
| Density | 1.2 | g/cm ³ | ISO 1183 |
| Water Absorption, (23°C/saturated) | 0.35 | % | ISO 62-1 |
| Melt Volume Rate, MVR at 300°C/1.2 kg | 6 | cm ³ /10 min | ISO 1133 |

OPTICAL

| | | | |
|-----------------------------|-------|---|------------|
| Light Transmission, 2.54 mm | 88-90 | % | ASTM D1003 |
| Haze, 2.54 mm | <0.8 | % | ASTM D1003 |
| Refractive Index | 1.586 | - | ASTM D542 |
| Refractive Index | 1.586 | - | ISO 489 |

ELECTRICAL

| | | | |
|------------------------------|---------|-------|-----------|
| Volume Resistivity | >1.E+15 | Ω.cm | ASTM D257 |
| Dielectric Strength, 1.6 mm | 27 | kV/mm | ASTM D149 |
| Relative Permittivity, 60 Hz | 3 | - | ASTM D150 |
| Relative Permittivity, 1 MHz | 3 | - | ASTM D150 |
| Dissipation Factor, 60 Hz | 0.001 | - | ASTM D150 |
| Dissipation Factor, 1 MHz | 0.01 | - | ASTM D150 |

| | | | |
|------------------------------|---------|-------|-------------|
| Volume Resistivity | >1.E+15 | Ω.cm | IEC 60093 |
| Dielectric Strength, 1.6 mm | 27 | kV/mm | IEC 60243-1 |
| Relative Permittivity, 60 Hz | 3 | - | IEC 60250 |
| Relative Permittivity, 1 MHz | 3 | - | IEC 60250 |
| Dissipation Factor, 60 Hz | 0.001 | - | IEC 60250 |
| Dissipation Factor, 1 MHz | 0.01 | - | IEC 60250 |
| Injection Molding | | | |
| Drying Temperature | 120 | °C | |
| Drying Time | 2-4 | Hrs | |
| Maximum Moisture Content | 0.02 | % | |
| Melt Temperature | 290-320 | °C | |
| Nozzle Temperature | 280-310 | °C | |
| Front - Zone 3 Temperature | 290-320 | °C | |
| Middle - Zone 2 Temperature | 280-310 | °C | |
| Rear - Zone 1 Temperature | 270-300 | °C | |
| Hopper Temperature | 60-80 | °C | |
| Mold Temperature | 80-120 | °C | |

此数据由我们从该材料的生产商处获得。我们尽最大努力确保此数据的准确性，但是我们对这些数据值不承担任何责任，并强烈建议在最终选料前，就数据值与材料供应商进行验证。