

SABIC LEXAN™ PC LUX2289物性表

| 属性 | 典型值 | UNITS | 测试手段 |
|--|------|-------------------|-------------|
| MECHANICAL | | | |
| Tensile Stress, yld, Type I, 50 mm/min | 60 | MPa | ASTM D638 |
| Tensile Stress, brk, Type I, 50 mm/min | 61 | MPa | ASTM D638 |
| Tensile Strain, yld, Type I, 50 mm/min | 6 | % | ASTM D638 |
| Tensile Strain, brk, Type I, 50 mm/min | 120 | % | ASTM D638 |
| Flexural Stress, yld, 1.3 mm/min, 50 mm span | 98 | MPa | ASTM D790 |
| Flexural Modulus, 1.3 mm/min, 50 mm span | 2670 | MPa | ASTM D790 |
| Tensile Stress, yield, 50 mm/min | 61 | MPa | ISO 527 |
| Tensile Stress, break, 50 mm/min | 62 | MPa | ISO 527 |
| Tensile Strain, yield, 50 mm/min | 6 | % | ISO 527 |
| Flexural Stress | 70 | MPa | ISO 178 |
| Flexural Modulus | 2500 | MPa | ISO 178 |
| IMPACT | | | |
| Izod Impact, unnotched, 23°C | 2130 | J/m | ASTM D4812 |
| Izod Impact, notched, 23°C | 648 | J/m | ASTM D256 |
| Izod Impact, notched, -30°C | 165 | J/m | ASTM D256 |
| Instrumented Dart Impact Total Energy, 23°C | 69 | J | ASTM D3763 |
| Izod Impact, unnotched 80*10*3 - 30°C | 160 | kJ/m ² | ISO 180/1U |
| Izod Impact, notched 80*10*3 +23°C | 52 | kJ/m ² | ISO 180/1A |
| Izod Impact, notched 80*10*3 - 30°C | 13 | kJ/m ² | ISO 180/1A |
| Izod Impact, unnotched 80*10*4 +23°C | 170 | kJ/m ² | ISO 180/1U |
| Charpy 23°C, V-notch Edgew 80*10*3 sp=62mm | 67 | kJ/m ² | ISO 179/1eA |
| Charpy -30°C, V-notch Edgew 80*10*3 sp=62mm | 12 | kJ/m ² | ISO 179/1eA |

| | | | | |
|--|------------------|--|-------------------------|----------------|
| Charpy 23°C, Unnotch Edgew 80*10*3 sp=62mm | 140 | | kJ/m ² | ISO 179/1eU |
| Charpy -30°C, Unnotch Edgew 80*10*3 sp=62mm | 140 | | kJ/m ² | ISO 179/1eU |
| THERMAL | | | | |
| Vicat Softening Temp, Rate B/50 | 142 | | °C | ASTM D1525 |
| HDT, 0.45 MPa, 3.2 mm, unannealed | 136 | | °C | ASTM D648 |
| HDT, 1.82 MPa, 3.2mm, unannealed | 124 | | °C | ASTM D648 |
| CTE, -40°C to 40°C, flow | 6.E-05 | | 1/°C | ASTM E831 |
| CTE, -40°C to 40°C, xflow | 6.3E-05 | | 1/°C | ASTM E831 |
| Vicat Softening Temp, Rate A/50 | 144 | | °C | ISO 306 |
| Vicat Softening Temp, Rate B/50 | 145 | | °C | ISO 306 |
| HDT/Ae, 1.8 MPa Annealed 120°C, 2hrs | 123 | | °C | ISO 75/Ae |
| PHYSICAL | | | | |
| Specific Gravity | 1.34 | | - | ASTM D792 |
| Mold Shrinkage, flow, 3.2 mm | 0.5-0.7 | | % | SABIC method |
| Melt Flow Rate, 300°C/1.2 kgf | 17 | | g/10 min | ASTM D1238 |
| Density | 1.31 | | g/cm ³ | ISO 1183 |
| Water Absorption, (23°C/saturated) | 0.35 | | % | ISO 62-1 |
| Moisture Absorption (23°C / 50% RH) | 0.15 | | % | ISO 62 |
| Melt Volume Rate, MVR at 300°C/1.2 kg | 16 | | cm ³ /10 min | ISO 1133 |
| FLAME CHARACTERISTICS | | | | |
| UL Yellow Card Link | E45329-101527188 | | - | - |
| UL Recognized, 94HB Flame Class Rating | 1 | | mm | UL 94 |
| UL Recognized, 94V-2 Flame Class Rating | 1.5 | | mm | UL 94 |
| Glow Wire Flammability Index 960°C, passes at | 1 | | mm | IEC 60695-2-12 |
| Glow Wire Ignitability Temperature, 1.0 mm | 850 | | °C | IEC 60695-2-13 |
| Injection Molding | | | | |
| Drying Temperature | 120 | | °C | |
| Drying Time | 3-4 | | Hrs | |

| | | |
|-----------------------------|-------------|-----|
| Drying Time (Cumulative) | 48 | Hrs |
| Maximum Moisture Content | 0.02 | % |
| Melt Temperature | 280-305 | °C |
| Nozzle Temperature | 275-300 | °C |
| Front - Zone 3 Temperature | 280-305 | °C |
| Middle - Zone 2 Temperature | 270-295 | °C |
| Rear - Zone 1 Temperature | 260-280 | °C |
| Mold Temperature | 70-95 | °C |
| Back Pressure | 0.3-0.7 | MPa |
| Screw Speed | 40-70 | rpm |
| Shot to Cylinder Size | 40-60 | % |
| Vent Depth | 0.025-0.076 | mm |

此数据由我们从该材料的生产商处获得。我们尽最大努力确保此数据的准确性，但是我们对这些数据值不承担任何责任，并强烈建议在最终选料前，就数据值与材料供应商进行验证。