

# SABIC LEXAN™ PC HFR1723物性表

属性	典型值	UNITS	测试手段
<b>MECHANICAL</b>			
Tensile Stress, yld, Type I, 50 mm/min	62	MPa	ASTM D638
Tensile Stress, brk, Type I, 50 mm/min	65	MPa	ASTM D638
Tensile Strain, brk, Type I, 50 mm/min	110	%	ASTM D638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	93	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	2300	MPa	ASTM D790
<b>IMPACT</b>			
Izod Impact, notched, 23°C	640	J/m	ASTM D256
Tensile Impact Strength, Type S	378	kJ/m <sup>2</sup>	ASTM D1822
Instrumented Dart Impact Energy @ peak, 23°C	54	J	ASTM D3763
<b>THERMAL</b>			
HDT, 1.82 MPa, 6.4 mm, unannealed	126	°C	ASTM D648
Relative Temp Index, Elec	130	°C	UL 746B
Relative Temp Index, Mech w/impact	130	°C	UL 746B
Relative Temp Index, Mech w/o impact	130	°C	UL 746B
<b>PHYSICAL</b>			
Specific Gravity	1.2	-	ASTM D792
Mold Shrinkage, flow, 3.2 mm	0.5-0.7	%	SABIC method
Melt Flow Rate, 300°C/1.2 kgf	25	g/10 min	ASTM D1238
<b>OPTICAL</b>			
Light Transmission, 2.54 mm	88	%	ASTM D1003
Haze, 2.54 mm	1	%	ASTM D1003
<b>FLAME CHARACTERISTICS</b>			
UL Yellow Card Link	E121562-220946	-	-

UL Recognized, 94V-2 Flame Class Rating	1.2	mm	UL 94
<b>Injection Molding</b>			
Drying Temperature	120	°C	
Drying Time	3-4	Hrs	
Drying Time (Cumulative)	48	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	270-295	°C	
Nozzle Temperature	265-290	°C	
Front - Zone 3 Temperature	270-295	°C	
Middle - Zone 2 Temperature	260-280	°C	
Rear - Zone 1 Temperature	250-270	°C	
Mold Temperature	70-95	°C	
Back Pressure	0.3-0.7	MPa	
Screw Speed	40-70	rpm	
Shot to Cylinder Size	40-60	%	
Vent Depth	0.025-0.076	mm	

此数据由我们从该材料的生产商处获得。我们尽最大努力确保此数据的准确性，但是我们对这些数据值不承担任何责任，并强烈建议在最终选料前，就数据值与材料供应商进行验证。