

# SABIC XENOY™ PBT/PC 5720U物性表

属性	典型值	UNITS	测试手段
<b>MECHANICAL</b>			
Tensile Stress, yld, Type I, 50 mm/min	47	MPa	ASTM D638
Tensile Stress, brk, Type I, 50 mm/min	48	MPa	ASTM D638
Tensile Stress, yld, Type I, 5 mm/min	44	MPa	ASTM D638
Tensile Stress, brk, Type I, 5 mm/min	50	MPa	ASTM D638
Tensile Stress, yld, Type I, 10 mm/min	45	MPa	SABIC - Japan Method
Tensile Stress, brk, Type I, 10 mm/min	47	MPa	SABIC - Japan Method
Tensile Strain, yld, Type I, 50 mm/min	4	%	ASTM D638
Tensile Strain, brk, Type I, 50 mm/min	116.6	%	ASTM D638
Tensile Strain, yld, Type I, 5 mm/min	4.6	%	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	122.4	%	ASTM D638
Tensile Strain, yld, Type I, 10 mm/min	4.6	%	SABIC - Japan Method
Tensile Strain, brk, Type I, 10 mm/min	109.5	%	SABIC - Japan Method
Tensile Modulus, 50 mm/min	1810	MPa	ASTM D638
Tensile Modulus, 5 mm/min	1830	MPa	ASTM D638
Tensile Modulus, 10 mm/min	1830	MPa	SABIC - Japan Method
Flexural Stress, yld, 1.3 mm/min, 50 mm span	70	MPa	ASTM D790
Flexural Stress, brk, 1.3 mm/min, 50 mm span	69	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	1660	MPa	ASTM D790
Tensile Stress, yield, 5 mm/min	44	MPa	ISO 527
Tensile Stress, break, 5 mm/min	43	MPa	ISO 527
Tensile Stress, yield, 50 mm/min	47	MPa	ISO 527

Tensile Stress, break, 50 mm/min	43	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	4.1	%	ISO 527
Tensile Strain, break, 5 mm/min	106.8	%	ISO 527
Tensile Strain, yield, 50 mm/min	4.6	%	ISO 527
Tensile Strain, break, 50 mm/min	115.3	%	ISO 527
Tensile Modulus, 1 mm/min	1790	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	71	MPa	ISO 178
Flexural Modulus, 2 mm/min	1860	MPa	ISO 178
<b>IMPACT</b>			
Izod Impact, notched, 23°C	722	J/m	ASTM D256
Izod Impact, notched, 0°C	691	J/m	ASTM D256
Izod Impact, notched, -10°C	663	J/m	ASTM D256
Izod Impact, notched, -20°C	695	J/m	ASTM D256
Izod Impact, notched, -30°C	647	J/m	ASTM D256
Izod Impact, notched, -40°C	598	J/m	ASTM D256
Instrumented Dart Impact Energy @ peak, 23°C	44	J	ASTM D3763
Instrumented Impact, Energy @ peak, -20°C	41	J	ASTM D3763
Instrumented Dart Impact Energy @ peak, -30°C	49	J	ASTM D3763
Instrumented Impact Energy @ peak, -40°C	49	J	ASTM D3763
Instrumented Dart Impact Total Energy, 23°C	54	J	ASTM D3763
Instrumented Impact Total Energy, -20°C	53	J	ASTM D3763
Instrumented Dart Impact Total Energy, -30°C	61	J	ASTM D3763
Instrumented Impact Total Energy, -40°C	59	J	ASTM D3763
Izod Impact, notched 80*10*4 +23°C	55	kJ/m <sup>2</sup>	ISO 180/1A
Izod Impact, notched 80*10*4 0°C	55	kJ/m <sup>2</sup>	ISO 180/1A
Izod Impact, notched 80*10*4 -10°C	52	kJ/m <sup>2</sup>	ISO 180/1A
Izod Impact, notched 80*10*4 -20°C	50	kJ/m <sup>2</sup>	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	48	kJ/m <sup>2</sup>	ISO 180/1A

Izod Impact, notched 80*10*4 - 40°C	46		kJ/m <sup>2</sup>	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	55		kJ/m <sup>2</sup>	ISO 179/1eA
Charpy -30°C, V-notch Edgew 80*10*4 sp=62mm	47		kJ/m <sup>2</sup>	ISO 179/1eA
<b>THERMAL</b>				
Vicat Softening Temp, Rate B/50	119		°C	ASTM D1525
HDT, 0.45 MPa, 3.2 mm, unannealed	108		°C	ASTM D648
HDT, 1.82 MPa, 3.2mm, unannealed	83		°C	ASTM D648
HDT, 0.45 MPa, 6.4 mm, unannealed	117		°C	ASTM D648
HDT, 1.82 MPa, 6.4 mm, unannealed	95		°C	ASTM D648
CTE, -40°C to 95°C, flow	9.75E-05		1/°C	ASTM E831
CTE, -40°C to 95°C, xflow	1.E-04		1/°C	ASTM E831
CTE, -30°C to 80°C, flow	9.75E-05		1/°C	ISO 11359-2
CTE, -30°C to 80°C, xflow	1.E-04		1/°C	ISO 11359-2
Vicat Softening Temp, Rate B/50	119		°C	ISO 306
Vicat Softening Temp, Rate B/120	122		°C	ISO 306
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	109		°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	87		°C	ISO 75/Af
<b>PHYSICAL</b>				
Specific Gravity	1.17		-	ASTM D792
Specific Volume	0.85		cm <sup>3</sup> /g	ASTM D792
Density	1.17		g/cm <sup>3</sup>	ASTM D792
Mold Shrinkage, flow, 3.2 mm	1-1.2		%	SABIC method
Melt Flow Rate, 250°C/2.16 kgf	3.8		g/10 min	ASTM D1238
Melt Flow Rate, 250°C/5.0 kgf	11.4		g/10 min	ASTM D1238
Melt Flow Rate, 265°C/2.16kgf	6		g/10 min	ASTM D1238
Melt Flow Rate, 266°C/5.0 kgf	19.7		g/10 min	ASTM D1238
Density	1.17		g/cm <sup>3</sup>	ISO 1183
Water Absorption, (23°C/saturated)	0.28		%	ISO 62-1
Moisture Absorption (23°C / 50% RH)	0.08		%	ISO 62

Melt Flow Rate, 250°C/2.16 kg	3	g/10 min	ISO 1133
Melt Flow Rate, 250°C/5.0 kg	11	g/10 min	ISO 1133
Melt Volume Rate, MVR at 250°C/2.16 kg	3	cm <sup>3</sup> /10 min	ISO 1133
Melt Volume Rate, MVR at 250°C/5.0 kg	10	cm <sup>3</sup> /10 min	ISO 1133
Melt Volume Rate, MVR at 265°C/2.16 kg	6	cm <sup>3</sup> /10 min	ISO 1133
Melt Volume Rate, MVR at 265°C/5.0 kg	18	cm <sup>3</sup> /10 min	ISO 1133

## FLAME CHARACTERISTICS

UL Yellow Card Link	E207780-100980305	-	-
---------------------	-------------------	---	---

## Injection Molding

Drying Temperature	110	°C
Drying Time	4-6	Hrs
Drying Time (Cumulative)	8	Hrs
Maximum Moisture Content	0.02	%
Melt Temperature	260-275	°C
Nozzle Temperature	255-270	°C
Front - Zone 3 Temperature	255-275	°C
Middle - Zone 2 Temperature	250-270	°C
Rear - Zone 1 Temperature	245-265	°C
Mold Temperature	65-90	°C
Back Pressure	0.3-0.7	MPa
Screw Speed	50-80	rpm
Shot to Cylinder Size	50-80	%
Vent Depth	0.013-0.02	mm

此数据由我们从该材料的生产商处获得。我们尽最大努力确保此数据的准确性，但是我们对这些数据值不承担任何责任，并强烈建议在最终选料前，就数据值与材料供应商进行验证。