

SABIC VALOX™ PBT 815物性表

属性	典型值	UNITS	测试手段
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	100	MPa	ASTM D638
Tensile Stress, brk, Type I, 5 mm/min	100	MPa	ASTM D638
Tensile Strain, yld, Type I, 50 mm/min	3	%	ASTM D638
Tensile Strain, brk, Type I, 50 mm/min	3	%	ASTM D638
Tensile Modulus, 5 mm/min	6200	MPa	ASTM D638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	155	MPa	ASTM D790
Flexural Stress, brk, 1.3 mm/min, 50 mm span	155	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	5000	MPa	ASTM D790
Hardness, Rockwell R	120	-	ASTM D785
Taber Abrasion, CS-17, 1 kg	17	mg/1000cy	SABIC method
Tensile Stress, yield, 5 mm/min	100	MPa	ISO 527
Tensile Stress, break, 5 mm/min	100	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	3	%	ISO 527
Tensile Strain, break, 5 mm/min	3	%	ISO 527
Tensile Modulus, 1 mm/min	6200	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	150	MPa	ISO 178
Flexural Stress, break, 2 mm/min	145	MPa	ISO 178
Flexural Strain, break, 2 mm/min	4	%	ISO 178
Flexural Modulus, 2 mm/min	5200	MPa	ISO 178
Ball Indentation Hardness, H358/30	102	MPa	ISO 2039-1
Hardness, Rockwell R	120	-	ISO 2039-2
IMPACT			
Charpy Impact, unnotched, 23°C	30	kJ/m ²	ISO 179/2C
Charpy Impact, unnotched, -30°C	30	kJ/m ²	ISO 179/2C
Izod Impact, unnotched, 23°C	390	J/m	ASTM D4812
Izod Impact, unnotched, -30°C	390	J/m	ASTM D4812

Izod Impact, notched, 23°C	60	J/m	ASTM D256
Izod Impact, notched, 0°C	60	J/m	ASTM D256
Izod Impact, notched, -30°C	60	J/m	ASTM D256
Izod Impact, unnotched 80*10*4 +23°C	30	kJ/m ²	ISO 180/1U
Izod Impact, unnotched 80*10*4 -30°C	25	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	6	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 0°C	6	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	6	kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	5	kJ/m ²	ISO 179/1eA
Charpy Impact, notched, 23°C	7	kJ/m ²	ISO 179/2C
Charpy -30°C, V-notch Edgew 80*10*4 sp=62mm	4	kJ/m ²	ISO 179/1eA
Charpy Impact, notched, -20°C	7	kJ/m ²	ISO 179/2C
Charpy 23°C, Unnotch Edgew 80*10*4 sp=62mm	30	kJ/m ²	ISO 179/1eU
Charpy -30°C, Unnotch Edgew 80*10*4 sp=62mm	30	kJ/m ²	ISO 179/1eU
THERMAL			
Vicat Softening Temp, Rate A/50	220	°C	ASTM D1525
Vicat Softening Temp, Rate B/50	204	°C	ASTM D1525
HDT, 0.45 MPa, 6.4 mm, unannealed	210	°C	ASTM D648
HDT, 1.82 MPa, 6.4 mm, unannealed	160	°C	ASTM D648
CTE, -40°C to 40°C, flow	4.5E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, xflow	9.32E-05	1/°C	ASTM E831
CTE, 60°C to 138°C, flow	5.4E-05	1/°C	ASTM E831
Thermal Conductivity	0.19	W/m-°C	ISO 8302
CTE, -40°C to 40°C, flow	3.23E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	7.2E-05	1/°C	ISO 11359-2
CTE, 23°C to 80°C, flow	5.5E-05	1/°C	ISO 11359-2
CTE, 23°C to 80°C, xflow	8.5E-05	1/°C	ISO 11359-2
CTE, 23°C to 150°C, flow	2.41E-05	1/°C	ISO 11359-2
CTE, 23°C to 150°C, xflow	1.76E-04	1/°C	ISO 11359-2

Ball Pressure Test, 125°C +/- 2°C	PASSES	-	IEC 60695-10-2
Vicat Softening Temp, Rate A/50	220	°C	ISO 306
Vicat Softening Temp, Rate B/50	204	°C	ISO 306
Vicat Softening Temp, Rate B/120	200	°C	ISO 306
HDT/Be, 0.45MPa Edgew 120*10*4 sp=100mm	210	°C	ISO 75/Be
HDT/Ae, 1.8 MPa Edgew 120*10*4 sp=100mm	175	°C	ISO 75/Ae
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	210	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	167	°C	ISO 75/Af
Relative Temp Index, Elec	125	°C	UL 746B
Relative Temp Index, Mech w/impact	110	°C	UL 746B
Relative Temp Index, Mech w/o impact	125	°C	UL 746B
PHYSICAL			
Specific Gravity	1.43	-	ASTM D792
Specific Volume	0.7	cm ³ /g	ASTM D792
Water Absorption, (23°C/24hrs)	0.06	%	ASTM D570
Mold Shrinkage on Tensile Bar, flow	0.4-0.8	%	SABIC method
Mold Shrinkage, flow, 1.5-3.2 mm	0.4-0.6	%	SABIC method
Mold Shrinkage, flow, 3.2-4.6 mm	0.6-0.9	%	SABIC method
Mold Shrinkage on Tensile Bar, xflow	0.6-1	%	SABIC method
Mold Shrinkage, xflow, 1.5-3.2 mm	0.5-0.8	%	SABIC method
Mold Shrinkage, xflow, 3.2-4.6 mm	0.8-1.1	%	SABIC method
Melt Flow Rate, 250°C/5.0 kgf	20	g/10 min	ASTM D1238
Melt Flow Rate, 265°C/5.0 kgf	60	g/10 min	ASTM D1238
Density	1.43	g/cm ³	ISO 1183
Water Absorption, (23°C/saturated)	0.26	%	ISO 62-1
Moisture Absorption (23°C / 50% RH)	0.06	%	ISO 62
Melt Volume Rate, MVR at 265°C/1.2 kg	12	cm ³ /10 min	ISO 1133
Melt Volume Rate, MVR at 265°C/5.0 kg	50	cm ³ /10 min	ISO 1133
Melt Viscosity, 260°C, 1500 sec-1	155	Pa-s	ISO 11443

ELECTRICAL

Volume Resistivity	5.6E+16	Ω.cm	ASTM D257
Dielectric Strength, in air, 3.2 mm	22	kV/mm	ASTM D149
Dielectric Strength, in oil, 1.6 mm	23.6	kV/mm	ASTM D149
Relative Permittivity, 100 Hz	3.6	-	ASTM D150
Relative Permittivity, 1 MHz	3.5	-	ASTM D150
Dissipation Factor, 100 Hz	0.002	-	ASTM D150
Arc Resistance, Tungsten {PLC}	5	PLC Code	ASTM D495
Hot Wire Ignition {PLC}	2	PLC Code	UL 746A
High Voltage Arc Track Rate {PLC}	1	PLC Code	UL 746A
High Ampere Arc Ign, surface {PLC}	2	PLC Code	UL 746A
Comparative Tracking Index (UL) {PLC}	2	PLC Code	UL 746A
Volume Resistivity	>1.E+15	Ω.cm	IEC 60093
Surface Resistivity, ROA	>1.E+15	Ω	IEC 60093
Dielectric Strength, shorttime, 1.0mm	18	kV/mm	IEC 60243-1
Dielectric Strength, in oil, 0.8 mm	30	kV/mm	IEC 60243-1
Dielectric Strength, in oil, 1.6 mm	24	kV/mm	IEC 60243-1
Dielectric Strength, in oil, 3.2 mm	16	kV/mm	IEC 60243-1
Relative Permittivity, 100 Hz	3.6	-	IEC 60250
Relative Permittivity, 1 MHz	2.9	-	IEC 60250
Dissipation Factor, 50/60 Hz	0.001	-	IEC 60250
Dissipation Factor, 100 Hz	0.002	-	IEC 60250
Dissipation Factor, 1 MHz	0.02	-	IEC 60250
Comparative Tracking Index	325	V	IEC 60112
Comparative Tracking Index, M	175	V	IEC 60112
Relative Permittivity, 50/60 Hz	3	-	IEC 60250

FLAME CHARACTERISTICS

UL Yellow Card Link	E45329-236632	-	-
UL Recognized, 94HB Flame Class Rating	1.5	mm	UL 94
UL Recognized, 94HB Flame Class Rating 2nd value	3	mm	UL 94
Glow Wire Flammability Index 750°C, passes at	1	mm	IEC 60695-2-12

Injection Molding		
Drying Temperature	110-120	°C
Drying Time	4-6	Hrs
Maximum Moisture Content	0.02	%
Melt Temperature	260-285	°C
Nozzle Temperature	265-275	°C
Front - Zone 3 Temperature	260-280	°C
Middle - Zone 2 Temperature	255-280	°C
Rear - Zone 1 Temperature	240-260	°C
Hopper Temperature	40-60	°C
Mold Temperature	60-110	°C

此数据由我们从该材料的生产商处获得。我们尽最大努力确保此数据的准确性，但是我们对这些数据值不承担任何责任，并强烈建议在最终选料前，就数据值与材料供应商进行验证。