

SABIC VALOX™ PBT 420物性表

属性	典型值	UNITS	测试手段
MECHANICAL			
Tensile Stress, brk, Type I, 5 mm/min	119	MPa	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	3	%	ASTM D638
Flexural Stress, brk, 1.3 mm/min, 50 mm span	190	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	7580	MPa	ASTM D790
Hardness, Rockwell R	118	-	ASTM D785
IMPACT			
Izod Impact, unnotched, 23°C	801	J/m	ASTM D4812
Izod Impact, notched, 23°C	85	J/m	ASTM D256
THERMAL			
HDT, 0.45 MPa, 6.4 mm, unannealed	215	°C	ASTM D648
HDT, 1.82 MPa, 6.4 mm, unannealed	207	°C	ASTM D648
CTE, -40°C to 40°C, flow	2.52E-05	1/°C	ASTM E831
CTE, 60°C to 138°C, flow	2.52E-05	1/°C	ASTM E831
Relative Temp Index, Elec	140	°C	UL 746B
Relative Temp Index, Mech w/impact	140	°C	UL 746B
Relative Temp Index, Mech w/o impact	140	°C	UL 746B
PHYSICAL			
Specific Gravity	1.53	-	ASTM D792
Specific Volume	0.66	cm ³ /g	ASTM D792
Water Absorption, (23°C/24hrs)	0.06	%	ASTM D570
Mold Shrinkage, flow, 1.5-3.2 mm	0.3-0.5	%	SABIC method
Mold Shrinkage, flow, 3.2-4.6 mm	0.5-0.8	%	SABIC method
Mold Shrinkage, xflow, 1.5-3.2 mm	0.4-0.6	%	SABIC method
Mold Shrinkage, xflow, 3.2-4.6 mm	0.6-0.9	%	SABIC method

ELECTRICAL			
Volume Resistivity	>3.2E+16	Ω.cm	ASTM D257
Dielectric Strength, in air, 3.2 mm	18.7	kV/mm	ASTM D149
Dielectric Strength, in oil, 1.6 mm	24	kV/mm	ASTM D149
Relative Permittivity, 100 Hz	3.8	-	ASTM D150
Relative Permittivity, 1 MHz	3.7	-	ASTM D150
Dissipation Factor, 100 Hz	0.002	-	ASTM D150
Dissipation Factor, 1 MHz	0.02	-	ASTM D150
Arc Resistance, Tungsten {PLC}	5	PLC Code	ASTM D495
High Voltage Arc Track Rate {PLC}	1	PLC Code	UL 746A
Comparative Tracking Index (UL) {PLC}	0	PLC Code	UL 746A

FLAME CHARACTERISTICS			
UL Yellow Card Link	E207780-100173314	-	-
UL Yellow Card Link 2	E45587-236813	-	-
UL Recognized, 94HB Flame Class Rating	0.83	mm	UL 94
Oxygen Index (LOI)	19	%	ASTM D2863

Injection Molding			
Drying Temperature	120	°C	
Drying Time	3-4	Hrs	
Drying Time (Cumulative)	12	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	250-265	°C	
Nozzle Temperature	245-260	°C	
Front - Zone 3 Temperature	250-265	°C	
Middle - Zone 2 Temperature	245-260	°C	
Rear - Zone 1 Temperature	240-255	°C	
Mold Temperature	65-90	°C	
Back Pressure	0.3-0.7	MPa	
Screw Speed	50-80	rpm	
Shot to Cylinder Size	40-80	%	
Vent Depth	0.025-0.038	mm	

此数据由我们从该材料的生产商处获得。我们尽最大努力确保此数据的准确性，但是我们对这些数据

值不承担任何责任，并强烈建议在最终选料前，就数据值与材料供应商进行验证。