

SABIC CYCOLOY™ PC/ABS HC1204HF物性表

属性	典型值	UNITS	测试手段
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	57	MPa	ASTM D638
Tensile Stress, brk, Type I, 50 mm/min	47	MPa	ASTM D638
Tensile Strain, yld, Type I, 50 mm/min	5	%	ASTM D638
Tensile Strain, brk, Type I, 50 mm/min	100	%	ASTM D638
Tensile Modulus, 5 mm/min	2270	MPa	ASTM D638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	88	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	2300	MPa	ASTM D790
Taber Abrasion, CS-17, 1 kg	63	mg/1000cy	SABIC method
Tensile Stress, yield, 5 mm/min	55	MPa	ISO 527
Tensile Stress, break, 5 mm/min	45	MPa	ISO 527
Tensile Stress, yield, 50 mm/min	55	MPa	ISO 527
Tensile Stress, break, 50 mm/min	45	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	5	%	ISO 527
Tensile Strain, break, 5 mm/min	100	%	ISO 527
Tensile Strain, yield, 50 mm/min	4	%	ISO 527
Tensile Strain, break, 50 mm/min	>50	%	ISO 527
Tensile Modulus, 1 mm/min	2400	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	80	MPa	ISO 178
Flexural Modulus, 2 mm/min	2300	MPa	ISO 178
Ball Indentation Hardness, H358/30	96	MPa	ISO 2039-1
Hardness, Rockwell R	115	-	ISO 2039-2
IMPACT			
Izod Impact, notched, 23°C	580	J/m	ASTM D256
Izod Impact, notched, -30°C	480	J/m	ASTM D256
Instrumented Dart Impact Total Energy, 23°C	54	J	ASTM D3763

Izod Impact, unnotched 80*10*4 +23°C	NB		kJ/m ²	ISO 180/1U
Izod Impact, unnotched 80*10*4 -30°C	NB		kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	40		kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	20		kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	45		kJ/m ²	ISO 179/1eA
Charpy -30°C, V-notch Edgew 80*10*4 sp=62mm	18		kJ/m ²	ISO 179/1eA
Charpy 23°C, Unnotch Edgew 80*10*4 sp=62mm	NB		kJ/m ²	ISO 179/1eU
Charpy -30°C, Unnotch Edgew 80*10*4 sp=62mm	NB		kJ/m ²	ISO 179/1eU
THERMAL				
Vicat Softening Temp, Rate B/50	130		°C	ASTM D1525
HDT, 1.82 MPa, 3.2mm, unannealed	112		°C	ASTM D648
CTE, -40°C to 40°C, flow	7.2E-05		1/°C	ASTM E831
CTE, -40°C to 40°C, xflow	7.2E-05		1/°C	ASTM E831
Thermal Conductivity	0.2		W/m-°C	ISO 8302
CTE, 23°C to 60°C, flow	8.E-05		1/°C	ISO 11359-2
CTE, 23°C to 60°C, xflow	8.E-05		1/°C	ISO 11359-2
Ball Pressure Test, 125°C +/- 2°C	PASSES		-	IEC 60695-10-2
Vicat Softening Temp, Rate B/50	126		°C	ISO 306
Vicat Softening Temp, Rate B/120	128		°C	ISO 306
HDT/Be, 0.45MPa Edgew 120*10*4 sp=100mm	122		°C	ISO 75/Be
HDT/Ae, 1.8 MPa Edgew 120*10*4 sp=100mm	102		°C	ISO 75/Ae
Relative Temp Index, Elec	105		°C	UL 746B
Relative Temp Index, Mech w/impact	80		°C	UL 746B
Relative Temp Index, Mech w/o impact	105		°C	UL 746B
PHYSICAL				
Specific Gravity	1.15		-	ASTM D792
Mold Shrinkage on Tensile Bar, flow	0.5-0.7		%	SABIC method

Mold Shrinkage, flow, 3.2 mm	0.5-0.7	%	SABIC method
Melt Flow Rate, 260°C/5.0 kgf	24	g/10 min	ASTM D1238
Density	1.15	g/cm ³	ISO 1183
Water Absorption, (23°C/saturated)	0.6	%	ISO 62-1
Moisture Absorption (23°C / 50% RH)	0.2	%	ISO 62
Melt Volume Rate, MVR at 260°C/2.16 kg	8	cm ³ /10 min	ISO 1133
Melt Volume Rate, MVR at 260°C/5.0 kg	22	cm ³ /10 min	ISO 1133

ELECTRICAL

Volume Resistivity	>1.E+15	Ω.cm	IEC 60093
Surface Resistivity, ROA	>1.E+15	Ω	IEC 60093
Dielectric Strength, in oil, 0.8 mm	35	kV/mm	IEC 60243-1
Dielectric Strength, in oil, 1.6 mm	25	kV/mm	IEC 60243-1
Dielectric Strength, in oil, 3.2 mm	17	kV/mm	IEC 60243-1
Relative Permittivity, 1 MHz	2.7	-	IEC 60250
Dissipation Factor, 50/60 Hz	0.002	-	IEC 60250
Dissipation Factor, 1 MHz	0.007	-	IEC 60250
Comparative Tracking Index	250	V	IEC 60112
Relative Permittivity, 50/60 Hz	2.8	-	IEC 60250

FLAME CHARACTERISTICS

UL Yellow Card Link	E45329-236710	-	-
UL Recognized, 94HB Flame Class Rating	1.2	mm	UL 94
UL Recognized, 94HB Flame Class Rating 2nd value	3	mm	UL 94
Glow Wire Flammability Index 650°C, passes at	1	mm	IEC 60695-2-12
Oxygen Index (LOI)	23	%	ISO 4589

Injection Molding

Drying Temperature	100-110	°C
Drying Time	2-4	Hrs
Maximum Moisture Content	0.02	%
Melt Temperature	260-290	°C
Nozzle Temperature	240-280	°C
Front - Zone 3 Temperature	250-290	°C

Middle - Zone 2 Temperature	250-290	°C
Rear - Zone 1 Temperature	230-260	°C
Hopper Temperature	60-80	°C
Mold Temperature	60-90	°C

此数据由我们从该材料的生产商处获得。我们尽最大努力确保此数据的准确性，但是我们对这些数据值不承担任何责任，并强烈建议在最终选料前，就数据值与材料供应商进行验证。