

SABIC XENOY™ PBT/PC 1102物性表

属性	典型值	UNITS	测试手段
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	54	MPa	ASTM D638
Tensile Strain, brk, Type I, 50 mm/min	150	%	ASTM D638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	82	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	1960	MPa	ASTM D790
Tensile Stress, yield, 50 mm/min	50	MPa	ISO 527
Tensile Stress, break, 50 mm/min	45	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	4.5	%	ISO 527
Tensile Strain, break, 50 mm/min	115	%	ISO 527
Flexural Stress, yield, 2 mm/min	72	MPa	ISO 178
Flexural Modulus, 2 mm/min	1870	MPa	ISO 178
IMPACT			
Izod Impact, notched, 23°C	800	J/m	ASTM D256
Izod Impact, notched, 0°C	690	J/m	ASTM D256
Izod Impact, notched, -30°C	640	J/m	ASTM D256
Izod Impact, notched 80*10*4 +23°C	54	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 0°C	52	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	44	kJ/m ²	ISO 180/1A
THERMAL			
HDT, 0.45 MPa, 6.4 mm, unannealed	110	°C	ASTM D648
HDT, 1.82 MPa, 6.4 mm, unannealed	90	°C	ASTM D648
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	79	°C	ISO 75/Af
PHYSICAL			
Specific Gravity	1.19	-	ASTM D792
Specific Volume	0.83	cm ³ /g	ASTM D792

Mold Shrinkage, flow, 3.2 mm	0.8-1	%	SABIC method
Mold Shrinkage, xflow, 3.2 mm	0.8-1	%	SABIC method
Density	1.19	g/cm ³	ISO 1183
Melt Volume Rate, MVR at 250°C/2.16 kg	6	cm ³ /10 min	ISO 1133
FLAME CHARACTERISTICS			
UL Yellow Card Link	E207780-100080987	-	-
Injection Molding			
Drying Temperature	110	°C	
Drying Time	4-6	Hrs	
Drying Time (Cumulative)	8	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	260-275	°C	
Nozzle Temperature	255-270	°C	
Front - Zone 3 Temperature	255-275	°C	
Middle - Zone 2 Temperature	250-270	°C	
Rear - Zone 1 Temperature	245-265	°C	
Mold Temperature	65-90	°C	
Back Pressure	0.3-0.7	MPa	
Screw Speed	50-80	rpm	
Shot to Cylinder Size	50-80	%	
Vent Depth	0.013-0.02	mm	

此数据由我们从该材料的生产商处获得。我们尽最大努力确保此数据的准确性，但是我们对这些数据值不承担任何责任，并强烈建议在最终选料前，就数据值与材料供应商进行验证。