

# SABIC XENOY™ PBT/PC CL101物性表

属性	典型值	UNITS	测试手段
<b>MECHANICAL</b>			
Tensile Stress, yld, Type I, 50 mm/min	53	MPa	ASTM D638
Tensile Stress, brk, Type I, 50 mm/min	49	MPa	ASTM D638
Tensile Strain, yld, Type I, 50 mm/min	4.5	%	ASTM D638
Tensile Strain, brk, Type I, 50 mm/min	50	%	ASTM D638
Tensile Modulus, 50 mm/min	2050	MPa	ASTM D638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	75	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	2000	MPa	ASTM D790
Taber Abrasion, CS-17, 1 kg	30	mg/1000cy	SABIC method
Tensile Stress, yield, 50 mm/min	52	MPa	ISO 527
Tensile Stress, break, 50 mm/min	44	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	4.5	%	ISO 527
Tensile Strain, break, 50 mm/min	50	%	ISO 527
Tensile Modulus, 1 mm/min	2050	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	75	MPa	ISO 178
Flexural Modulus, 2 mm/min	2000	MPa	ISO 178
Ball Indentation Hardness, H358/30	82	MPa	ISO 2039-1
Hardness, Rockwell L	89	-	ISO 2039-2
<b>IMPACT</b>			
Izod Impact, notched, 23°C	625	J/m	ASTM D256
Izod Impact, notched, 0°C	600	J/m	ASTM D256
Izod Impact, notched, -30°C	450	J/m	ASTM D256
Izod Impact, unnotched 80*10*4 +23°C	NB	kJ/m <sup>2</sup>	ISO 180/1U
Izod Impact, unnotched 80*10*4 -30°C	NB	kJ/m <sup>2</sup>	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	50	kJ/m <sup>2</sup>	ISO 180/1A

Izod Impact, notched 80*10*4 - 30°C	35	kJ/m <sup>2</sup>	ISO 180/1A
Izod Impact, notched 80*10*4 - 40°C	25	kJ/m <sup>2</sup>	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	58	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy Impact, notched, 23°C	30	kJ/m <sup>2</sup>	ISO 179/2C
Charpy -30°C, V-notch Edgew 80*10*4 sp=62mm	25	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy Impact, notched, -20°C	25	kJ/m <sup>2</sup>	ISO 179/2C
Charpy Impact, notched, -30°C	20	kJ/m <sup>2</sup>	ISO 179/2C
Charpy 23°C, Unnotch Edgew 80*10*4 sp=62mm	NB	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy -30°C, Unnotch Edgew 80*10*4 sp=62mm	NB	kJ/m <sup>2</sup>	ISO 179/1eU
<b>THERMAL</b>			
Vicat Softening Temp, Rate B/50	120	°C	ASTM D1525
HDT, 1.82 MPa, 3.2mm, unannealed	83	°C	ASTM D648
CTE, -40°C to 40°C, flow	9.E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, xflow	9.5E-05	1/°C	ASTM E831
Thermal Conductivity	0.18	W/m-°C	ISO 8302
CTE, 23°C to 80°C, flow	9.E-05	1/°C	ISO 11359-2
CTE, 23°C to 80°C, xflow	9.5E-05	1/°C	ISO 11359-2
Ball Pressure Test, 75°C +/- 2°C	PASSES	-	IEC 60695-10-2
Vicat Softening Temp, Rate A/50	155	°C	ISO 306
Vicat Softening Temp, Rate B/50	120	°C	ISO 306
Vicat Softening Temp, Rate B/120	123	°C	ISO 306
HDT/Be, 0.45MPa Edgew 120*10*4 sp=100mm	105	°C	ISO 75/Be
HDT/Ae, 1.8 MPa Edgew 120*10*4 sp=100mm	83	°C	ISO 75/Ae
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	105	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	83	°C	ISO 75/Af
<b>PHYSICAL</b>			
Specific Gravity	1.22	-	ASTM D792
Mold Shrinkage on Tensile Bar, flow	0.7-1.1	%	SABIC method

Mold Shrinkage on Tensile Bar, xflow	0.7-1.1	%	SABIC method
Melt Flow Rate, 250°C/5.0 kgf	14	g/10 min	ASTM D1238
Density	1.22	g/cm <sup>3</sup>	ISO 1183
Water Absorption, (23°C/saturated)	0.5	%	ISO 62-1
Moisture Absorption (23°C / 50% RH)	0.15	%	ISO 62
Melt Volume Rate, MVR at 250°C/5.0 kg	13	cm <sup>3</sup> /10 min	ISO 1133
<b>ELECTRICAL</b>			
Volume Resistivity	>1.E+14	Ω.cm	IEC 60093
Surface Resistivity, ROA	>1.E+15	Ω	IEC 60093
Dielectric Strength, shorttime, 1.0mm	18	kV/mm	IEC 60243-1
Dielectric Strength, in oil, 3.2 mm	17	kV/mm	IEC 60243-1
Relative Permittivity, 1 MHz	3.3	-	IEC 60250
Dissipation Factor, 50/60 Hz	0.002	-	IEC 60250
Dissipation Factor, 1 MHz	0.02	-	IEC 60250
Relative Permittivity, 50/60 Hz	3.3	-	IEC 60250
<b>FLAME CHARACTERISTICS</b>			
UL Compliant, 94HB Flame Class Rating	1.5	mm	UL 94 by SABIC-IP
<b>Injection Molding</b>			
Drying Temperature	90 - 100	°C	
Drying Time	2 - 4	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	255 - 270	°C	
Nozzle Temperature	250 - 265	°C	
Front - Zone 3 Temperature	250 - 270	°C	
Middle - Zone 2 Temperature	240 - 265	°C	
Rear - Zone 1 Temperature	230 - 250	°C	
Hopper Temperature	40 - 60	°C	
Mold Temperature	60 - 80	°C	

此数据由我们从该材料的生产商处获得。我们尽最大努力确保此数据的准确性，但是我们对这些数据值不承担任何责任，并强烈建议在最终选料前，就数据值与材料供应商进行验证。