

SABIC LEXAN™ PC 143R物性表

属性	典型值	UNITS	测试手段
MECHANICAL			
Taber Abrasion, CS-17, 1 kg	10	mg/1000cy	SABIC method
Tensile Stress, yield, 50 mm/min	63	MPa	ISO 527
Tensile Stress, break, 50 mm/min	70	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	6	%	ISO 527
Tensile Strain, break, 50 mm/min	110	%	ISO 527
Tensile Modulus, 1 mm/min	2350	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	90	MPa	ISO 178
Flexural Modulus, 2 mm/min	2300	MPa	ISO 178
Ball Indentation Hardness, H358/30	95	MPa	ISO 2039-1
IMPACT			
Izod Impact, unnotched 80*10*3 +23°C	NB	kJ/m ²	ISO 180/1U
Izod Impact, unnotched 80*10*3 -30°C	NB	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*3 +23°C	70	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*3 -30°C	12	kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*3 sp=62mm	73	kJ/m ²	ISO 179/1eA
Charpy -30°C, V-notch Edgew 80*10*3 sp=62mm	14	kJ/m ²	ISO 179/1eA
Charpy 23°C, Unnotch Edgew 80*10*3 sp=62mm	NB	kJ/m ²	ISO 179/1eU
Charpy -30°C, Unnotch Edgew 80*10*3 sp=62mm	NB	kJ/m ²	ISO 179/1eU
Charpy Impact, notched, 23°C	35	kJ/m ²	ISO 179/2C
THERMAL			
Thermal Conductivity	0.2	W/m-°C	ISO 8302
CTE, 23°C to 80°C, flow	7.E-05	1/°C	ISO 11359-2
Ball Pressure Test, 125°C +/- 2°C	PASSES	-	IEC 60695-10-2
Ball Pressure Test, approximate maximum	140	°C	IEC 60695-10-2

Vicat Softening Temp, Rate A/50	153	°C	ISO 306
Vicat Softening Temp, Rate B/50	141	°C	ISO 306
Vicat Softening Temp, Rate B/120	142	°C	ISO 306
HDT/Be, 0.45MPa Edgew 120*10*4 sp=100mm	136	°C	ISO 75/Be
HDT/Ae, 1.8 MPa Edgew 120*10*4 sp=100mm	125	°C	ISO 75/Ae
Relative Temp Index, Elec	130	°C	UL 746B
Relative Temp Index, Mech w/impact	125	°C	UL 746B
Relative Temp Index, Mech w/o impact	125	°C	UL 746B
PHYSICAL			
Mold Shrinkage on Tensile Bar, flow	0.5-0.7	%	SABIC method
Density	1.2	g/cm ³	ISO 1183
Water Absorption, (23°C/saturated)	0.35	%	ISO 62-1
Moisture Absorption (23°C / 50% RH)	0.15	%	ISO 62
Melt Volume Rate, MVR at 300°C/1.2 kg	12	cm ³ /10 min	ISO 1133
OPTICAL			
Light Transmission, 2.54 mm	88-90	%	ASTM D1003
Haze, 2.54 mm	<0.8	%	ASTM D1003
Refractive Index	1.586	-	ISO 489
ELECTRICAL			
Volume Resistivity	>1.E+15	Ω.cm	IEC 60093
Surface Resistivity, ROA	>1.E+15	Ω	IEC 60093
Dielectric Strength, shorttime, 1.0mm	15	kV/mm	IEC 60243-1
Dielectric Strength, in oil, 3.2 mm	17	kV/mm	IEC 60243-1
Relative Permittivity, 1 MHz	2.7	-	IEC 60250
Dissipation Factor, 50/60 Hz	0.001	-	IEC 60250
Dissipation Factor, 1 MHz	0.01	-	IEC 60250
Comparative Tracking Index	250	V	IEC 60112
Relative Permittivity, 50/60 Hz	2.7	-	IEC 60250
FLAME CHARACTERISTICS			

UL Yellow Card Link	E45329-101012967	-	-
UL Yellow Card Link 2	E45329-236637	-	-
UL Recognized, 94HB Flame Class Rating	0.75	mm	UL 94
UL Recognized, 94HB Flame Class Rating 2nd value	3	mm	UL 94
Glow Wire Flammability Index 850°C, passes at	1	mm	IEC 60695-2-12
Oxygen Index (LOI)	25	%	ISO 4589

Injection Molding

Drying Temperature	120	°C
Drying Time	2-4	Hrs
Maximum Moisture Content	0.02	%
Melt Temperature	280-310	°C
Nozzle Temperature	270-290	°C
Front - Zone 3 Temperature	280-310	°C
Middle - Zone 2 Temperature	270-290	°C
Rear - Zone 1 Temperature	260-280	°C
Hopper Temperature	60-80	°C
Mold Temperature	80-110	°C

此数据由我们从该材料的生产商处获得。我们尽最大努力确保此数据的准确性，但是我们对这些数据值不承担任何责任，并强烈建议在最终选料前，就数据值与材料供应商进行验证。