

# SABIC VALOX™ PBT 4012G物性表

属性	典型值	UNITS	测试手段
<b>MECHANICAL</b>			
Tensile Stress, yld, Type I, 5 mm/min	80	MPa	ASTM D638
Tensile Stress, brk, Type I, 5 mm/min	80	MPa	ASTM D638
Tensile Strain, yld, Type I, 5 mm/min	3	%	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	3	%	ASTM D638
Tensile Modulus, 5 mm/min	4400	MPa	ASTM D638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	120	MPa	ASTM D790
Flexural Stress, brk, 1.3 mm/min, 50 mm span	120	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	3800	MPa	ASTM D790
Tensile Stress, yield, 5 mm/min	80	MPa	ISO 527
Tensile Stress, break, 5 mm/min	80	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	3	%	ISO 527
Tensile Strain, break, 5 mm/min	3	%	ISO 527
Tensile Modulus, 1 mm/min	4500	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	125	MPa	ISO 178
Flexural Stress, break, 2 mm/min	120	MPa	ISO 178
Flexural Strain, break, 2 mm/min	5	%	ISO 178
Flexural Modulus, 2 mm/min	3800	MPa	ISO 178
Ball Indentation Hardness, H358/30	110	MPa	ISO 2039-1
Hardness, Rockwell R	120	-	ISO 2039-2
<b>IMPACT</b>			
Charpy Impact, unnotched, 23°C	33	kJ/m <sup>2</sup>	ISO 179/2C
Charpy Impact, unnotched, -30°C	33	kJ/m <sup>2</sup>	ISO 179/2C
Izod Impact, unnotched, 23°C	380	J/m	ASTM D4812
Izod Impact, unnotched, -30°C	380	J/m	ASTM D4812
Izod Impact, notched, 23°C	50	J/m	ASTM D256
Izod Impact, notched, 0°C	50	J/m	ASTM D256

Izod Impact, notched, -30°C	50	J/m	ASTM D256
Instrumented Dart Impact Total Energy, 23°C	4	J	ASTM D3763
Izod Impact, unnotched 80*10*4 +23°C	35	kJ/m <sup>2</sup>	ISO 180/1U
Izod Impact, unnotched 80*10*4 - 30°C	30	kJ/m <sup>2</sup>	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	5	kJ/m <sup>2</sup>	ISO 180/1A
Izod Impact, notched 80*10*4 0°C	5	kJ/m <sup>2</sup>	ISO 180/1A
Izod Impact, notched 80*10*4 - 30°C	5	kJ/m <sup>2</sup>	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	7	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy Impact, notched, 23°C	6	kJ/m <sup>2</sup>	ISO 179/2C
Charpy -30°C, V-notch Edgew 80*10*4 sp=62mm	6	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy Impact, notched, -30°C	6	kJ/m <sup>2</sup>	ISO 179/2C
Charpy 23°C, Unnotch Edgew 80*10*4 sp=62mm	45	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy -30°C, Unnotch Edgew 80*10*4 sp=62mm	45	kJ/m <sup>2</sup>	ISO 179/1eU
<b>THERMAL</b>			
Vicat Softening Temp, Rate A/50	220	°C	ASTM D1525
Vicat Softening Temp, Rate B/50	205	°C	ASTM D1525
HDT, 0.45 MPa, 3.2 mm, unannealed	215	°C	ASTM D648
HDT, 1.82 MPa, 3.2mm, unannealed	190	°C	ASTM D648
CTE, -40°C to 40°C, flow	6.E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, xflow	8.E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, flow	4.63E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	8.2E-05	1/°C	ISO 11359-2
CTE, 23°C to 80°C, flow	6.E-05	1/°C	ISO 11359-2
CTE, 23°C to 80°C, xflow	8.E-05	1/°C	ISO 11359-2
CTE, 23°C to 150°C, flow	4.79E-05	1/°C	ISO 11359-2
CTE, 23°C to 150°C, xflow	2.11E-04	1/°C	ISO 11359-2
Ball Pressure Test, 125°C +/- 2°C	PASSES	-	IEC 60695-10-2
Vicat Softening Temp, Rate A/50	220	°C	ISO 306
Vicat Softening Temp, Rate B/50	205	°C	ISO 306

Vicat Softening Temp, Rate B/120	200	°C	ISO 306
HDT/Be, 0.45MPa Edgew 120*10*4 sp=100mm	215	°C	ISO 75/Be
HDT/Ae, 1.8 MPa Edgew 120*10*4 sp=100mm	170	°C	ISO 75/Ae
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	215	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	185	°C	ISO 75/Af

## PHYSICAL

Specific Gravity	1.35	-	ASTM D792
Filler Content	10	%	ASTM D229
Mold Shrinkage on Tensile Bar, flow	0.6-0.9	%	SABIC method
Mold Shrinkage, flow, 3.2 mm	0.6-1.6	%	SABIC method
Mold Shrinkage on Tensile Bar, xflow	0.7-1	%	SABIC method
Melt Flow Rate, 250°C/1.2 kgf	10	g/10 min	ASTM D1238
Melt Flow Rate, 266°C/5.0 kgf	90	g/10 min	ASTM D1238
Density	1.35	g/cm <sup>3</sup>	ISO 1183
Water Absorption, (23°C/saturated)	0.2	%	ISO 62-1
Moisture Absorption (23°C / 50% RH)	0.07	%	ISO 62
Melt Volume Rate, MVR at 250°C/1.2 kg	9	cm <sup>3</sup> /10 min	ISO 1133
Melt Volume Rate, MVR at 250°C/5.0 kg	50	cm <sup>3</sup> /10 min	ISO 1133
Melt Volume Rate, MVR at 265°C/5.0 kg	80	cm <sup>3</sup> /10 min	ISO 1133
Melt Viscosity, 260°C, 1500 sec-1	110	Pa-s	ISO 11443

## ELECTRICAL

Volume Resistivity	>1.E+15	Ω.cm	ASTM D257
Dielectric Strength, in oil, 0.8 mm	30	kV/mm	ASTM D149
Dielectric Strength, in oil, 1.6 mm	23	kV/mm	ASTM D149
Dielectric Strength, in oil, 3.2 mm	18	kV/mm	ASTM D149
Relative Permittivity, 1 MHz	3.4	-	ASTM D150
Dissipation Factor, 1 MHz	0.015	-	ASTM D150
Volume Resistivity	>1.E+15	Ω.cm	IEC 60093
Surface Resistivity, ROA	>1.E+15	Ω	IEC 60093

Dielectric Strength, in oil, 0.8 mm	30	kV/mm	IEC 60243-1
Dielectric Strength, in oil, 1.6 mm	23	kV/mm	IEC 60243-1
Dielectric Strength, in oil, 3.2 mm	18	kV/mm	IEC 60243-1
Relative Permittivity, 1 MHz	3.4	-	IEC 60250
Dissipation Factor, 50/60 Hz	0.001	-	IEC 60250
Dissipation Factor, 1 MHz	0.015	-	IEC 60250
Comparative Tracking Index	325	V	IEC 60112
Comparative Tracking Index, M	150	V	IEC 60112
Relative Permittivity, 50/60 Hz	3.1	-	IEC 60250
<b>FLAME CHARACTERISTICS</b>			
UL Compliant, 94HB Flame Class Rating	1.6	mm	UL 94 by SABIC-IP
Glow Wire Flammability Index 750°C, passes at	1	mm	IEC 60695-2-12
Glow Wire Ignitability Temperature, 1.0 mm	775	°C	IEC 60695-2-13
Glow Wire Ignitability Temperature, 1.5 mm	800	°C	IEC 60695-2-13
Glow Wire Ignitability Temperature, 2.0 mm	775	°C	IEC 60695-2-13
Glow Wire Ignitability Temperature, 3.0 mm	750	°C	IEC 60695-2-13
<b>Injection Molding</b>			
Drying Temperature	110-120	°C	
Drying Time	2-4	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	250-270	°C	
Nozzle Temperature	240-260	°C	
Front - Zone 3 Temperature	245-265	°C	
Middle - Zone 2 Temperature	240-255	°C	
Rear - Zone 1 Temperature	230-245	°C	
Hopper Temperature	40-60	°C	
Mold Temperature	40-100	°C	

此数据由我们从该材料的生产商处获得。我们尽最大努力确保此数据的准确性，但是我们对这些数据值不承担任何责任，并强烈建议在最终选料前，就数据值与材料供应商进行验证。