

SABIC CYCOLAC™ ABS FR23物性表

属性	典型值	UNITS	测试手段
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	42	MPa	ASTM D638
Tensile Stress, brk, Type I, 5 mm/min	35	MPa	ASTM D638
Tensile Strain, yld, Type I, 5 mm/min	2.1	%	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	11	%	ASTM D638
Tensile Modulus, 5 mm/min	2410	MPa	ASTM D638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	73	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	2720	MPa	ASTM D790
IMPACT			
Izod Impact, notched, 23°C	267	J/m	ASTM D256
Instrumented Dart Impact Total Energy, 23°C	41	J	ASTM D3763
THERMAL			
Vicat Softening Temp, Rate B/50	90	°C	ASTM D1525
HDT, 0.45 MPa, 3.2 mm, unannealed	83	°C	ASTM D648
HDT, 1.82 MPa, 3.2mm, unannealed	72	°C	ASTM D648
CTE, -40°C to 40°C, flow	7.92E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, xflow	7.92E-05	1/°C	ASTM E831
Relative Temp Index, Elec	60	°C	UL 746B
Relative Temp Index, Mech w/impact	60	°C	UL 746B
Relative Temp Index, Mech w/o impact	60	°C	UL 746B
PHYSICAL			
Specific Gravity	1.17	-	ASTM D792
Mold Shrinkage, flow, 3.2 mm	0.5-0.7	%	SABIC method
Melt Flow Rate, 230°C/3.8 kg	6.8	g/10 min	ASTM D1238

Melt Viscosity, 200°C, 1000 sec-1	3100	Poise	ASTM D3825
Melt Flow Rate, 220°C/5.0 kg	9	g/10 min	ISO 1133
Melt Volume Rate, MVR at 220°C/10.0 kg	37	cm ³ /10 min	ISO 1133
FLAME CHARACTERISTICS			
UL Yellow Card Link	E207780-228348	-	-
UL Recognized, 94V-0 Flame Class Rating	2.31	mm	UL 94
UL Recognized, 94-5VB Flame Class Rating	2.48	mm	UL 94

此数据由我们从该材料的生产商处获得。我们尽最大努力确保此数据的准确性，但是我们对这些数据值不承担任何责任，并强烈建议在最终选料前，就数据值与材料供应商进行验证。